

DERWENT-ACC-NO: 1986-128541

DERWENT-WEEK: 198620

COPYRIGHT 1999 DERWENT INFORMATION LTD

TITLE: Super-high mol. wt. polyethylene film
prepn. - by forming dispersion in organic solvent,
heating, extruding, solvent evaporation and
cooling

PATENT-ASSIGNEE: MITSUBISHI MONSANTO KK[MITT]

PRIORITY-DATA: 1984JP-0190403 (September 11, 1984)

PATENT-FAMILY:

PUB-NO	PAGES	MAIN-IPC	PUB-DATE	LANGUAGE
JP 61066624 A	006	N/A	April 5, 1986	N/A
JP 92047608 B	005	B29C 047/78	August 4, 1992	N/A

APPLICATION-DATA:

PUB-NO	APPL-DATE	APPL-DESCRIPTOR	APPL-NO
JP 61066624A	September 11, 1984	N/A	1984JP-0190403
JP 92047608B	September 11, 1984	N/A	1984JP-0190403
JP 92047608B	N/A	Based on	JP 61066624

INT-CL (IPC): B29C047/40, B29C047/78, B29C047/92,
B29K023/00,
B29K023:00, B29L007/00, B29L007:00, C08J003/20,
C08J005/18

ABSTRACTED-PUB-NO: JP 61066624A

BASIC-ABSTRACT:

Film or sheet of super-high mol. wt. polyethylene having ave.

mol. wt. of at
least 1,000,000 is prepd. by (A) adding super-high mol. wt.
polyethylene to
organic solvent to provide dispersion or mixt. contg. 10-80
wt.% of the
polyethylene, (B) heating this dispersion or mixt. at a temp.
at least the
m.pt. of the dispersion or mixt. to melt it and extruding the
dispersion into
film or sheet through biaxial extruder, (C) evaporating the
organic solvent by
heating the film or sheet and (D) cooling the film or sheet.

The organic solvent is pref. p-xylene, decalin, octalin,
tetrachloroethane, for
dissolving or swelling the polyethylene.

USE/ADVANTAGE - The process provides efficiently high mol.
wt. polyethylene
film or sheet having smooth surface.

In an example polyethylene (Hi-zex Million 240M having wt.
ave. mol. wt. of
about 3,000,000 and ave. particle size of about 100 micron
and available from
MITC) was added to p-xylene to the concn. of 50 wt.%, at room
temp., to provide
slurry. The slurry has peak temp. of 120 deg.C, as measured
by differential
scanning calorimeter in accordance with ASTM D 3417-82. The
slurry was
extruded through biaxial extruder having slit die, at
cylinder temp. of 180
deg.C, die temp. of 200 deg.C, 10 rpm. and extruding rate of
0.2 kg/min. to
provide 1.2 mm-thick and 40 mm-wide sheet. The sheet was
heated in an oven at
180 deg.C for 10 min. to evaporate p-xylene and then cooled
to provide
polyethylene sheet having thickness of 1.15 mm and width of
38 mm.

CHOSEN-DRAWING: Dwg.0/0

TITLE-TERMS: SUPER HIGH MOLECULAR WEIGHT POLYETHYLENE FILM
PREPARATION FORMING
DISPERSE ORGANIC SOLVENT HEAT EXTRUDE SOLVENT
EVAPORATION COOLING

DERWENT-CLASS: A17 A32

CPI-CODES: A04-G02C; A11-A; A11-B07A; A11-B07D; A12-S06A;
A12-S07;

POLYMER-MULTIPUNCH-CODES-AND-KEY-SERIALS:

Key Serials: 3003 0211 0229 0239 0247 2318 2336 2368 2375
2378 2386 2393 2451

2503 2507 2513 2522 2585 2661

Multipunch Codes: 014 03- 041 046 047 049 13- 316 332 369 392
397 398 402 408

409 414 415 42- 423 427 435 450 502 575 583 589 597 602 688
726

SECONDARY-ACC-NO:

CPI Secondary Accession Numbers: C1986-054907

	Type	L #	Hits	Search Text	DBs	Time Stamp	Comments
1	IS&R	L3	1	("5422061").PN.	USPAT; US-PGPUB	2003/07/29 11:58	
2	BRS	L4	3	"Hi-Zex 5000H" or "Sholex-SUPER"	USPAT; US-PGPUB; EPO; JPO; DERWENT	2003/07/29 11:05	
3	BRS	L5	115	"Hi-Zex" or "Sholex-SUPER"	USPAT; US-PGPUB; EPO; JPO; DERWENT	2003/07/29 11:08	
4	BRS	L6	1	"Sholex-SUPER"	USPAT; US-PGPUB; EPO; JPO; DERWENT	2003/07/29 11:14	
5	BRS	L7	2	"Lubmer L5000P"	USPAT; US-PGPUB; EPO; JPO; DERWENT	2003/07/29 11:15	
6	BRS	L8	2	"Lubmer L3000P"	USPAT; US-PGPUB; EPO; JPO; DERWENT	2003/07/29 11:22	

	Type	L #	Hits	Search Text	DBs	Time Stamp	Comments
7	BRS	L9	552498	polyethylene or (ethylene adj polymer) and (wear adj resistance)	USPAT; US-PGPUB; EPO; JPO; DERWENT	2003/07/29 11:29	
8	BRS	L10	259809	9 and sliding	USPAT; US-PGPUB; EPO; JPO; DERWENT	2003/07/29 11:31	
9	BRS	L11	1297	10 and (ultra adj high adj molecular adj weight)	USPAT; US-PGPUB; EPO; JPO; DERWENT	2003/07/29 11:29	
10	BRS	L12	5229	(polyethylene or (ethylene adj polymer)) same (ultra adj high adj molecular adj weight)	USPAT; US-PGPUB; EPO; JPO; DERWENT	2003/07/29 11:59	
11	BRS	L13	162	12 same (wear adj resistance)	USPAT; US-PGPUB; EPO; JPO; DERWENT	2003/07/29 11:31	

	Type	L #	Hits	Search Text	DBs	Time Stamp	Comments
12	BRS	L14	58	13 and sliding	USPAT; US-PGPUB; EPO; JPO; DERWENT	2003/07/29 11:31	
13	BRS	L15	2	(polyethylene or (ethylene adj polymer)) same (molecular adj weight) same (wear adj coefficient) and sliding	USPAT; US-PGPUB; EPO; JPO; DERWENT	2003/07/29 12:00	